

SPEKTRA antinicotine paint

USE

For the protection and decoration of interior wall and ceiling surfaces. It covers and isolates the spots caused by smoking, water outflow, tar, different oils, fire etc. Such spots are soluble in water, so water brings them to the surface during drying; therefore, the water-based paints are not suitable for covering these spots.

It is suitable for the painting of different types of mineral plasters, fibre-cement plates, concrete, plaster-cardboard plates, wall papers from glass fibres, wall papers with relief and old coatings.

CHARACTERISTICS

- On aromatics'-free solvent basis
- Without aggressive odour
- Excellent isolation of water-resistant spots
- Washable
- Easy application

TECHNICAL DATA

| | |
|----------------------------|--|
| PRODUCT TYPE | acrylic copolymer in organic solvent, pigments, fillers and special additives |
| COLOUR SHADES | white |
| TINTING | possible with colourants which are suitable for solvent-based paints (up to 3%) and with solvent based paints, up to 3% |
| GLOSS (EN 13300) | matt |
| DENSITY | 1,31 – 1,38 kg/l |
| WASHABILITY (EN 13300) | class 2 |
| THINNING | ready-to-use |
| EU VOC category and limits | IIA(g), 350 g/l (2010); the product contains: max. 350 g/l |
| PACKAGING | 0,75 l, 2,5 l and 20 l |
| SHELF LIFE | The shelf life of the originally closed and suitably packed product (temperature from +5°C to +35°C, in dry place) is until the date indicated on packaging. |

INSTRUCTIONS FOR USE

| | |
|-----------------------------------|--|
| APPLICATION | roller, brush, spraying |
| WORKING CONDITIONS | min. +5 °C air, surface and paint |
| DRYING (T = +20 °C, rel hum. 65%) | the coating is dry and suitable for overcoating after 6 hours |
| COVERAGE | Theoretically: 4 – 5 m ² with 1 l in 2 coats. Practical consumption depending on permeability and surface roughness. |
| CLEANING OF TOOLS | Immediately after use with SPEKTRA thinner for antinicotine paint . |

SURFACE PREPARATION

The surface should be free from dust, crumbly particles and other impurities. Remove old falling off coats. Fill up bigger cracks and damaged surface with adequate materials on the mineral basis. Prior to painting, the surface should be dry and cured.

Apply **SPEKTRA biocide agent SANITOL** to wall surfaces, which are attacked by mould and algae. After the surfaces have dried, remove mould mechanically. Use **SPEKTRA antimicrobial paint** as a final coating, which prevents the growth of mould and isolates the water-resistant spots.

Clean crack-free »healthy« surfaces, which are painted with smooth, gloss or semi-gloss enamels or dispersion paint and sand them with the sanding paper (No. 150).

COATING SYSTEMS

| SURFACE | SURFACE PREPARATION | PUTTYING | TOP COAT |
|---|--|---|--------------------------------------|
| New not painted surface - lime-cement plasters - plaster-cardboard plates - concrete and other not porous substrates | | 2x SPEKTRA interior putty (if necessary) | |
| Painted with dispersion paints - several layers of permeable, not washable coatings - smooth, shiny, washable coatings | cleaning, removal of crumbly particles, repair of damaged spots cleaning, polishing | 2x SPEKTRA interior putty (if necessary) | 2x SPEKTRA antinicotine paint |

REMARKS

- Mix paint thoroughly before use.
- Drying time increases at low temperatures and higher air humidity, it depends also on the surface roughness. The drying time is longer on the less permeable surfaces.
- Water-based wall paints can be applied over SPEKTRA antinicotine paint only after it is completely dry and hardened.
- In case of thinning the paint due to the application method, use SPEKTRA antinicotine paint thinner.